

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D01F 8/04, 8/12, 8/14, A46D 1/00, D01D 5/253	A1	(11) International Publication Number: WO 98/26117 (43) International Publication Date: 18 June 1998 (18.06.98)
(21) International Application Number: PCT/US97/22584 (22) International Filing Date: 10 December 1997 (10.12.97) (30) Priority Data: 08/766,218 12 December 1996 (12.12.96) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: NELSON, Charles, Fletcher; 67 Wildwood Drive, Parkersburg, WV 26101 (US). RACKLEY, Robert, Lee; 119 Canterbury Drive, Parkersburg, WV 26101 (US). (74) Agent: MOYLES, Lisa, J.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CN, JP, SG, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: COEXTRUDED MONOFILAMENTS (57) Abstract <p>This invention relates to a coextruded monofilament having a sheath made of a first resin and a core made of a second resin which is different than the first resin and which has a higher coefficient of friction than the first resin. The core of the monofilament is exposed at the tip by conventional mechanical end-rounding techniques to form a tip with a higher coefficient of friction than the tip of a typical monofilament.</p> <div data-bbox="1101 1144 1453 1911"></div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE

COEXTRUDED MONOFILAMENTS

5

BACKGROUND OF THE INVENTION

1. Field of the Invention

10 This invention relates to coextruded monofilaments which may be used, for example, in bristles for toothbrushes.

2. Description of the Related Art

15 Monofilaments made from nylon 6,12 or from polyester are typically circular in cross section with the tips of the monofilaments being well rounded. When used in toothbrushes, bristles made from monofilaments having rounded tips have been preferred because those bristles have a lower tendency to damage soft and hard oral tissue than bristles without rounded tips.

20

SUMMARY OF THE INVENTION

25 This invention relates to a coextruded monofilament having a sheath material made of a first resin and a core material made of a second resin which is different from the first resin and which has a higher coefficient of friction than the first resin. The core material is exposed at the tip of the monofilament by conventional mechanical end rounding techniques to form a tip that has a higher coefficient of friction than the rounded tip of a conventional monofilament.

30

BRIEF DESCRIPTION OF THE DRAWINGS

35 Figure 1 is a cross-sectional view in elevation of a coextruded monofilament made in accordance with this invention.

Figure 2 is a top plan view of the coextruded monofilament.

Figure 3 is a view in elevation of a conventional monofilament.

Figure 4 is a top plan view of the conventional monofilament of Figure 3; and

Figure 5 is a microscope photograph at approximately 75x of the tip of the coextruded monofilament of this invention.

DETAILED DESCRIPTION

This invention relates to a coextruded monofilament of a sheath material made from a first resin and a core material made of a second resin wherein the second resin is different from the first resin and has a higher coefficient of friction than the first resin. When the coextruded monofilament is inserted into a brush and the ends of the filament are trimmed and processed to expose the second resin on the tip of the filament. The tip of the filament then has a higher coefficient of friction than a conventional monofilament, while the filament itself maintains the excellent bend recovery properties of a conventional monofilament through the use of the first resin as the sheath of the coextruded monofilament. The purpose of the high coefficient of friction tip is to provide a better cleaning action than a conventional end-rounded monofilament. For example, if the coextruded monofilament is used as the bristle in a toothbrush, the high coefficient of friction tip will provide improved cleaning.

As used herein, the term "core" refers to the central portion of the coextruded monofilament as examined at a cross section. As used herein, the term "sheath" refers to an outer coating layer or layers over the core material on a coextruded monofilament.

Examples of combinations of sheath and core materials include a sheath material of nylon 6; 6,6; 6,10; 6,12; 6,9; 10,10; 11; 12; copolymers of nylons and mixtures thereof, and a core material of a copolyester ether such as that sold under the trademark Hytrel® by E.I. du Pont de Nemours and Company of Wilmington, Delaware.

Other examples of combinations of sheath and core materials include a sheath material of a nylon, a polyester, especially polyethylene terephthalate (PET) or polybutylene terephthalate (PBT), a polyurethane, polyvinylidene chloride, or polyvinylidene fluoride, or mixtures thereof,

and a core material of a thermoplastic elastomer such as a copolyester ether, polyether block amide, styrene block copolymer such as styrene-butadiene-styrene or styrene-ethylene-butylene-styrene, thermoplastic elastomer blend based on styrene block copolymer, thermoplastic polyolefin such as
5 ethylene propylene (diene) copolymer or blends thereof, or thermoplastic polyurethane, or mixtures thereof.

There is no limitation on the shape of the cross section of the core or the sheath of the coextruded monofilament. Either or both may be circular, triangular, square, pentagonal, hexagonal, any regular shaped polygon, oval,
10 lobate, or any other shape. The core may be hollow having either single or multiple voids, such as a trilocular or tetralocular cross section.

The cross-sectional area of the core material comprises from about 10 to about 90% of the cross-sectional area of the monofilament.

15

EXAMPLES

Example 1

Coextruded monofilaments having a core of Hytrel® 4056 copolyester ether and a sheath of 6,12 nylon were made using conventional methods. The monofilament was conditioned at 125°C by backwinding it
20 through a conditioner on a spinning line and then processed into hanks. The cross-sectional area of the core was about 55% of the total cross-sectional area of the monofilament.

These coextruded monofilaments were inserted into a tuft toothbrush and the ends of the monofilaments were subjected to
25 conventional end rounding, thus exposing the Hytrel® 4056 at the tips.

Coefficient of friction was measured for toothbrushes made of the coextruded monofilament and for toothbrushes made of 6,12 nylon monofilament. The toothbrushes were of the same design for both samples. Coefficient of friction was measured for the brush samples on glass. Four
30 toothbrushes containing a monofilament sample were mounted on a sled, which was loaded with a 1000 gram weight, and the assembly was pulled across a horizontal glass surface at the rate of 5 inches per minute with the tips of the filament in contact with the glass surface. The force required to move the brushes across the glass surface was measured with an INSTRON
35 tensile tester. The data below show a significantly higher coefficient of

friction for the brushes made with coextruded monofilament having a Hytrel® 4056 exposed at the tips of the bristles than for the brushes made with 6,12 nylon and having end-rounded tips.

5

	Coefficient of Friction		
	I	II	III
Toothbrushes made with coextruded monofilament	.36	.35	.37
Toothbrushes made with 6,12 nylon	.23	.30	.27
% increase in coefficient of friction	57%	17%	37%

WHAT IS CLAIMED IS:

1. A coextruded monofilament comprising:
 - a sheath material of a first resin,
 - 5 a core material of a second resin, the second resin being different from the first resin and having a higher coefficient of friction than the first resin,
 - wherein the core material is exposed at the end of the monofilament.
2. The coextruded monofilament of claim 1, wherein sheath
10 material is nylon 6; nylon 6,6; nylon 6,10; nylon 6,12; nylon 10,10; or copolymers of nylon 6 and 6,6; or mixtures thereof, and the core material is a copolyester ether.
3. The coextruded monofilament of claim 1, wherein the sheath
15 material is a nylon, a polyester, a polyurethane, polyvinylidene chloride, or polyvinylidene fluoride, or mixtures thereof, and the core material is a thermoplastic elastomer.
4. The coextruded monofilament of claim 1, wherein the core
material is a thermoplastic elastomer selected from the group consisting of
20 copolyester ether, polyether block amide, styrene block copolymer, thermoplastic elastomer blends based on styrene block copolymer, thermoplastic polyolefin or blends thereof, thermoplastic polyurethane, and mixtures thereof.
5. The coextruded monofilament of claim 1, wherein the
cross-sectional area of the core material comprises from about 10 to about
25 90% of the cross-sectional area of the monofilament.
6. The coextruded monofilament of claim 1, wherein the
cross-sectional shape of the sheath is circular, triangular, square,
pentagonal, hexagonal or oval.
7. The coextruded monofilament of claim 1, wherein the
30 cross-sectional shape of the core is circular, triangular, square, pentagonal, hexagonal, oval, or lobate.
8. The coextruded monofilament of claim 1, wherein the core has at
least one void formed therein.
9. A brush comprising a handle associated with a head having one or
35 more tufts made from the coextruded monofilament of any of claims 1-8.




FIG. 2



FIG. 4




FIG. 1




FIG. 3

2/2




FIG. 5

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 97/22584

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 D01F8/04 D01F8/12 D01F8/14 A46D1/00 D01D5/253

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D01F A46D D01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 263 691 A (PAKARNSEREE SEREE) 28 April 1981	1,5-7,9
Y	see the whole document	2-4,8
P,Y	WO 97 14830 A (E.I. DU PONT DE NEMOURS AND COMPANY) 24 April 1997 see the whole document	2-4,8
A	US 5 313 909 A (TSENG MINGCHIH M ET AL) 24 May 1994	
A	EP 0 663 162 A (PROCTER & GAMBLE) 19 July 1995	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

7 April 1998

Date of mailing of the international search report

24/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Tarrida Torrell, J

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/US 97/22584

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4263691 A	28-04-81	NONE	
WO 9714830 A	24-04-97	NONE	
US 5313909 A	24-05-94	AU 679015 B	19-06-97
		AU 5457594 A	24-05-94
		CN 1097969 A	01-02-95
		EP 0668991 A	30-08-95
		JP 8503145 T	09-04-96
		MX 9306881 A	30-06-94
		WO 9410539 A	11-05-94
		ZA 9308022 A	28-06-94
EP 0663162 A	19-07-95	WO 9519120 A	20-07-95

THIS PAGE BLANK (USPTO)